

Shield-Bright 309L X-tra

FCAW wire for 22%Cr - 12%Ni stainless steel For flat and horizontal position welding. Developed to be used when welding most mild or carbon steels to type 304. The higher percentages of Cr and Ni provide the necessary crack resistance. Carbon content 0.04% maximum.

Classifications	SFA/AWS A5.22 : E309LT0-1 SFA/AWS A5.22 : E309LT0-4 JIS Z 3323 : YF-309LC KS D 3612 : YF-309LC EN ISO 17633-A : T 23 12 L R C1 3 EN ISO 17633-A : T 23 12 L R M21 3
Approvals	ABS : E309LT0-1 BV : 309L (C1) CCS : 309LS (C1) CE : EN 13479 CWB : E309LT0-1 (C1) CWB : E309LT0-4 (M21) DNV : NV 309L MS (C1) DNV : NV 309L MS (M21) NAKS/HAKC : 1.2MM VdTÜV : 06594

Welding Current	DC+
Alloy Type	C Cr Ni

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
M21 Shielding Gas			
As Welded	480 MPa	600 MPa	35 %
C1 shielding gas			
As Welded	410 MPa	546 MPa	38 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
C1 shielding gas		
As Welded	-29 °C	40 J
As Welded	-196 °C	15 J

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr
M21 Shielding Gas						
0.030	1.44	0.80	0.004	0.020	13.0	24.50
C1 Shielding Gas						
0.032	1.46	0.66	0.004	0.021	12.8	24.50

Deposition Data

Diameter	Current	Voltage	Wire Feed Speed	Deposition Rate
1.2 mm	150-250 A	25-32 V	8.0-16.0 m/min	2.5-7.0 kg/h
1.6 mm	200-350 A	26-34 V	4.0-11.0 m/min	3.0-7.5 kg/h