

OK Tigrod 308L

Bare corrosion resisting chromium-nickel rods. OK Tigrod 308L has a good general corrosion resistance. The alloy has a low carbon content which makes this alloy particularly recommended where there is a risk of intergranular corrosion. The alloy is widely used in the chemical and food processing industries as well as for pipes, tubes and boilers. For joining of stainless steels of 18% Cr - 8% Ni-type with low carbon content and Nb-stabilized steels of the same type if the service temperature will not exceed 350°C. Can also be used for welding of Cr-steels except in sulphur rich environments.

Specifications

Classifications	EN ISO 14343-A : W 19 9 L SFA/AWS A5.9 : ER308L Werkstoffnummer : ~1.4316
Approvals	CE : EN 13479 CWB : ER308L DNV-GL : VL 308 L NAKS/HAKC : 1.6-2.4 mm VdTÜV : 04269

Alloy Type

Austenitic (with approx. 8 % ferrite) 19% Cr - 9% Ni - Low C

Typical Tensile Properties

Condition	Yield Strength	Tensile Strength	Elongation
As Welded	440 MPa	580 MPa	36 %

Typical Charpy V-Notch Properties

Condition	Testing Temperature	Impact Value
As Welded	20 °C	170 J
As Welded	-80 °C	135 J
As Welded	-196 °C	80 J

Typical Wire Composition %

C	Mn	Si	Ni	Cr	Mo	Cu	N	FN WRC-92
0.02	1.9	0.4	9.8	19.8	0.20	0.15	0.05	9

Typical Weld Metal Analysis %

C	Mn	Si	S	P	Ni	Cr	Mo	Cu
0.01	1.8	0.4	0.015	0.020	10	20	0.1	0.1