

**Classifications**

EN ISO 21952	EN ISO 636	AWS A5.28 / SFA-5.28
-A W MoSi	-A W 2Mo / W 46 3 2Mo	ER70S-A1 (ER80S-G)
-B W (1M3)	-B W 2M31 / W 55A 3U 2M31	

**Characteristics and typical fields of application**

TIG rod and wire for manual and mechanized gas tungsten arc welding. The 0.5Mo type weld metal microstructure exhibit acicular ferrite and bainite with favorable mechanical properties in the as welded and post weld heat treated condition. The range of application covers joint welding of similar alloyed creep resistant steel and steel casting up to joining of high strength structural, fine grained and pipeline steels. BÖHLER DMO-IG is approved for application under creep condition at design temperatures up to 550 °C.

**Base materials**

Similar creep resistant steels and cast steels, high strength structural, fine grained and pipeline steels like 16Mo3, 20MnMoNi4-5, 15NiCuMoNb5, S235JR-S355JR, S235J0-S355J0, S450J0, S235J2-S355J2, S275N-S460N, S275M-S460M, P235GH-P355GH, P355N, P285NH-P460NH, P195TR1-P265TR1, P195TR2-P265TR2, P195GH-P265GH, L245NB-L415NB, L450QB, L245MB-L450MB, GE200-GE300

ASTM A 29 Gr. 1013, 1016; A 106 Gr. C; A, B; A 182 Gr. F1; A 234 Gr. WP1; A 283 Gr. B, C, D; A 335 Gr. P1; A 501 Gr. B; A 533 Gr. B, C; A 510 Gr. 1013; A 512 Gr. 1021, 1026; A 513 Gr. 1021, 1026; A 516 Gr. 70; A 633 Gr. C; A 678 Gr. B; A 709 Gr. 36, 50; A 711 Gr. 1013; API 5 L B, X42, X52, X60, X65

**Typical analysis**

	C	Si	Mn	Mo
wt.-%	0.1	0.6	1.1	0.5


**Mechanical properties of all-weld metal - typical values (min. values)**

Condition	Yield strength $R_{p0.2}$	Tensile strength $R_m$	Elongation A ( $L_0=5d_0$ )	Impact energy ISO-V KV J	
	MPa	MPa	%	20 °C	-30 °C
U	530 (≥ 470)	650 (≥ 550 - 740)	26 (≥ 22)	180 (≥ 130)	100 (≥ 80)
SR	480 (≥ 470)	585 (≥ 550)	27 (≥ 22)	210 (≥ 150)	180 (≥ 130)

U: as welded

SR: stress relieved (620 °C / 1 h)

**Operating data**

	<b>Polarity</b>	DC -	<b>Dimension mm</b>
	<b>Shielding gas (EN ISO 14175)</b>	I1	0.8
	<b>Rod marking</b>	+ WMoSi / ER80S-G(A1)	1.0
			1.2
			1.6 x 1000
			2.0 x 1000/500
			2.4 x 1000
			3.0 x 1000
		3.2 x 1000	

Preheating, interpass temperature, and post-weld heat treatment as required by the base metal. Preheating can normally be recommended being in a range of 100 to 250 °C depending on the wall thickness. Common post weld heat treatments are carried out between 530 and 620 °C.

**Approvals**

TÜV (00020, 08066), DB (42.132.72), BV, DNV, CE